

TECHNICAL DATA SHEET

GZ-9090 HIGH SOLID 2K

CLEARCOAT



PRODUCT DESCRIPTION

■ Outline

GZ-9090 Supreme Gloss is an easy-applying clearcoat with excellent flow and melt-in properties. It is especially suitable for multi-panel repairs in the spray booth.

GZ-9090 Supreme Gloss is easy to apply and a high gloss acrylic urethane system with excellent durability. It matches with OEM basecoat/clearcoat.

■ Suitable Substrates

Basecoat OEM Finishes Fully-hardened two-component clearcoat (urethane, epoxy, etc.) Something made of plastic (bumper and the like)

■ Product Configuration

Product Name	Pack(ℓ)	Contents(ℓ)	Storage
Gloss Klarlack GZ-9090 Supreme	0.5	0.5	24 months
Gloss Klarlack GZ-9090 Supreme	1.0	1.0	24 months
Gloss Klarlack	5.0	5.0	24 months

* Standard temperature of storage is°C.
20

■ Mixing Viscosity

14~16 sec. Viscosity(A+B+T) Ford Cup #4 at 77°F (25°C)

■ Pot Life


4 hours at 77°F (25°C) after mixing



APPLICATION GUIDE


■ Use


Surface Preparation  Apply clearcoat after applying basecoat and wiping off the dust in the fully-dried condition.


Mixing Ratio 


Mixing Ratio	
Product code: GZ-9090 Product	2
code: GZ-9091/GZ-9092 Product	1
code: GZ-2030/2031/2032	0.2

* Mix by volume.

Spray Condition  2.0~2.5 bar (gravity feed) 2~3 wet coats keeping 20~25cm from the surface Fluid tip : 1.2~1.4mm, D.F.T.=50~60 μm

 3.0~4.0 bar (siphon feed) 2~3 wet coats keeping 20~25cm from the surface Fluid tip : 1.4~1.6mm, D.F.T.=50~60 μm

 0.6~0.7 bar (at nozzle) 2 wet coats keeping 20~25cm from the surface Fluid tip : 1.3~1.5mm, D.F.T.=50~60 μm

 Flash time : 10 min Set time : 10 min
Use fresh air mask or charcoal respirator to avoid inhaling or being exposed to fumes.

Protective Equipment



TECHNICAL DATA SHEET

GZ-9090 HIGH SOLID 2K

CLEARCOAT



■ Drying Times

	Temp	Time	Temp.	Time 70min	Remark
Time to dust free	25°C			24~48hrs	
Time to polish	25°C			24~48hrs	
Time to handle	25°C				

(*) If coats are thicker, the drying schedule will be delayed.

ADDITIONAL INFORMATION

- **Recoatability** 1) Recoatable time : 12 hours at ambient temperature after force dry 2) Sand and wipe off the dust with DR-180 before recoating.

* Do sand before recoating.



Dry sand P800



Wet sand P400 - P500

■ VOC

Content VOC content of 500g/liter
ISO 45001 and ISO 14001

■ Notice

1. For 2K products, short pot life, delayed drying time or unreactive substance can occur depending on hardener volume. Thus please mix base(A) and hardener(B) according to the proper mixing ratio. 2. Stir thoroughly before use. 3. Avoid direct sunlight during delivery, storage and handling. Store in a cool, dry dark place under room temperature(5°C-35°C). 4. Keep container tightly closed and store upright. When spilled, absorb contents with sand. 5. During application(including touch-up application), color difference may occur depending on mixing ratio, painting tools and application method. It may occur in same color product and same LOT No. 6. Please check whether color difference occurred or not. If possible, apply the same LOT No. product in consistent application method. 7. Putty marks might appear when you directly apply over the lacquer coating. As time goes by, it can peel off. 8. Completely eliminate the moisture of spray equipment before use. Cleanse immediately after application not to have any leftover on spray equipment. 9. Suitable condition for application and hardening is 10°C or above. 10. Surface temperature must be at or above 3°C to avoid moisture condensation. 11. Do not mix with other paint products. 12. Proceed a test application before applying on a precedent or an old paint film (check adhesion, color spread and transparency). 13. Please refer to technical data sheet before system application(primer, midcoat and topcoat). 14. Please do not apply paint above 85% RH or below 5°C because it may influence physical properties. 15. Contents must not flow into drain, river and soil. 16. Hardener must be stored under room temperature, avoid direct sunlight and keep away from humidity. 17. To prevent environmental pollution, dispose contents after complete use and dispose the residue through waste disposal company authorised by the ministry of environment. 18. Beware of ingestion, inhalation and contact of animals and plants. 19. Use masking tape, covering tape, vinyl or newspapers to cover areas that should not be painted.

TECHNICAL DATA SHEET

GZ-9090 HIGH SOLID 2K

CLEARCOAT



■ Health and Safety

1. Be well-informed of MSDS before use.
2. Keep out of the reach of infants and children. Do not apply a product to baby products and food containers.
3. Do not use a product for any other uses. (Sniffing is prohibited. Do not use as a fuel.)
4. If on skin or eye, wash thoroughly with running water and get a medical treatment.
5. Do not apply a product in an enclosed area.
In order to prevent suffocation during application and drying, use power blower to keep the area fully ventilated. Workers must wear gas mask and safety gears all the time.
6. Contents include organic solvents and can cause health problems such as headache, dizziness and dermatitis.
Do not ingest or inhale the product and avoid skin contact.
Wear safety glasses, coveralls and latex gloves when mixing and applying.
7. Keep away from fire and heat during application or storage because it is flammable and has risk of fire.
Beware of spark from impact, droppage and friction while handling.
8. Storing a product with combustible substances such as stained clothes or paper may cause fire by spontaneous ignition. Thus do not pile products with combustible substances.
Keep it in a non-flammable container filled with water, then put a lid on and dispose it.
9. Please contact our customer service or refer to GHS-MSDS and technical data on the website for further details.