

DESCRIPTION: **GLÄNZEND GZ-9701 UHS RAPID CLEARCOAT 4:1** is an economical double pack environment friendly acrylic clearcoat, easy application, durable gloss, fast drying, suitable for metallic basecoats. .

COMPONENTS: **GZ-9793 GZ-9793**

SUBSTRATES: 1K basecoat

SURFACE PREPARATION:

GZ-9701 UHS RAPID CLEAR 4:1

FastActivator

MediumActivator

SlowActivator

<64°F


64-86°F

>86°F



Remove wax, silicon or other contaminations with GZ-2062 degreaser.

MIX RATIO:



GZ-9701 4parts
GZ-9793 1part

POT LIFE:



2-3 hours with GZ-9793 @ 77°F

ADDITIVES:

Blushing: GZ-2039 REDUCER over 86°F.
Refer to tech sheet of Retarder Solvent for details.

Fisheyes: GZ-2077 Fisheye Eliminator (0.5-1%) in the paint remained and re-spray the affected area.

Overspray: GZ-2000 Thinner. Refer to techsheet of Thinner for details.

APPLICATION:




Spray gun set up:

Gravity feed (upper pot 1.2-1.5mm 3-5kg/cm²)
Siphon feed (below):
1.4-1.7mm 3-5kg/cm² pot

GZ-9701 ULTRA HIGH SOLID RAPID 2K CLEARCOAT

recommendations.



Coats: 2-3 coats, 40-60µm
Flash off time: 3-5 mins.
between coats @ 77°F
Air drying: allow 15-20 mins.
purge time before baking.

DRY TIME:



@ 77°F

Dust free: 35 minutes

Dry to Polish: 3 hours

@ 140°F

Dust free: 10 minutes

Dry to Polish: 20 minutes



CLEARNING:

Clean equipment immediately with solvent after application

Note:

When ambient temperature is lower than 41°F, to fast

the film drying time, allow a full bake at 140°F.

The products mixed with hardener should be used up

as soon as possible and not restore for future use.

Shelf Life: 2 years in original sealed can at cool and dry place at 68°F.

PHYSICAL DATA:

Regulatory VOC (RTS): 5.0 lbs/gal

FOR PROFESSIONAL USE ONLY Read MSDS

Before Use

NOTE: The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislations. The uncertain factors may affect the application of products, such as the condition of substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.